

TRUMP ECO TEK

60mil(1.5mm) HDPE TEXTURED GEOMEMBRANE



Trump Eco textured geomembrane is a co-extruded textured high-density polyethylene (HDPE) geomembrane available on one or both sides. It is manufactured with the highest quality resin specifically formulated for flexible geomembranes. This product is used in applications that require increased frictional resistance, excellent chemical resistance and endurance properties. This product specification meets GRI-GM13. Single Sided (SST) and Double Sided (DST).

TESTED PROPERTY	TEST METHOD	FREQUENCY	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Thickness (nominal)	ASTM D 5994	every roll	mil (mm)	60 (1.5)
Thickness (min avg)				57 (1.43)
Thickness (min 8 of 10)				54 (1.35)
Thickness (lowest individual)				51 (1.28)
Density	ASTM D 1505	200,000 lb (90,000 kg)	g/cc, min	0.94
Tensile Properties (Each Direction)	ASTM D 6693, Type IV Dumbbell, 2 ipm G.L. 2.0in (50mm) G.L. 1.3in (33mm)	20,000 lb (9,000 kg)	lb/in-width (N/mm)	132 (23.1)
Strength at Break			lb/in-width (N/mm)	132 (23.1)
Strength at Yield			%	350
Elongation at Break			%	13
Elongation at Yield				
Tear Resistance	ASTM D 1004	45,000 lb (20,000 kg)	lb (N)	45 (200)
Puncture Resistance	ASTM D 4833	45,000 lb (20,000 kg)	lb (N)	120 (534)
Carbon Black Content	ASTM D 4218	20,000 lb (9,000 kg)	% (range)	2-3
Carbon Black Dispersion	ASTM D 5596	45,000 lb (20,000 kg)		Note ⁽¹⁾
Asperity Height	ASTM D 7466	second roll	mil (mm)	20 (0.51)
Stress Crack Resistance (SP-NTCL)	ASTM D 5397, Appendix	200,000 lb (90,000 kg)	hrs	500
Oxidative Induction Time	ASTM D 3895, 200°C; O ₂ , 1 atm	200,000 lb (90,000 kg)	mins	≥140
TYPICAL ROLL DIMENSIONS				
Roll Length ⁽²⁾	Double-Sided Textured		ft (m)	164(50)
	Single-Sided Textured		ft (m)	164 (50)
Roll Width ⁽²⁾			ft (m)	19 (5.8)
Roll Area	Double-Sided Textured		ft ² (m ²)	3115 (290)
	Single-Sided Textured		ft ² (m ²)	3115(290)

Notes:

Roll Lengths and widths have a tolerance of ±1%.

HDPE SST/DST is available in rolls weighing approximately 959 lb (435 kg).

This data is provided for informational purposes only. Trump Eco makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

Geosynthetic Tek. Since 1983

Email: dennis@ecohdpe.com

Phone: +86 158.823.141.58 (whatsApp Wechat)

Web: www.ecoHDPE.com